

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **63-012156**

(43)Date of publication of application : **19.01.1988**

(51)Int.Cl.

H01L 21/90
H01L 21/30

(21)Application number : **61-156545**

(71)Applicant : **MITSUBISHI ELECTRIC CORP**

(22)Date of filing : **02.07.1986**

(72)Inventor : **OZAKI KATSUYA**
SASAKI YOSHINOBU

(54) MINUTE PATTERN FORMING METHOD

(57)Abstract:

PURPOSE: To form a three-dimensional minute pattern of a desired configuration in a simple and reproducible manner by depositing metal using a mask composed of a three-dimensional resist profile obtained by two exposure processes under different conditions.

CONSTITUTION: Positive type photoresist 6 is thickly applied on a GaAs substrate 1, on which an electrode 2 is formed. A converging ion beam is selectively projected, and a desired range of the resist 6 is exposed to a desired thickness. Then an ion beam accelerated by a voltage higher than that in the previous process is projected to the resist 6 in the range where the electrode 2 is formed. The resist 6 is exposed to the interface with the electrode 2. Then, development is performed, and a three-dimensional resist profile is obtained. Thereafter, metal is evaporated, and a metal deposited layer 7 is formed. Lift-off is performed, and a three-dimensional minute pattern is obtained. Thus, reproducibility is improved.

